



Technical datasheet No.: **1147.1**

Product: POLYMAR® scrim

Article No.: 7002 5300

Type of coating and finish			
Type of coating	PVC		
Total weight	400 g/m ²	EN ISO 2286-2	
Openess factor	45 %	LB 3.27	
Tensile strength (warp/weft)	3000 / 2000 N/50 mm	DIN 53354, DIN EN ISO 1421/V1	
Tear strength (1) (warp/weft)	400 / 290 N	DIN 53363	
Translucence	45 %	at 550 nm	
Light fastness	>6 Note, Val.	DIN 54004, DIN EN ISO 105 B02	
Air permeability	9400 l/m ² *sec	DIN EN ISO 9237	
Base fabric			
Material	PES	DIN ISO 2076	
Yarn count	3300 / 2200 dtex	DIN ISO 2060	

These indicated technical data are based on average results. Due to production procedures slight deviations can occur. All technical data are in accordance with the present standard of knowledge and give product information without legal binding. All data apply to new products. Applications suggested do not release the customer to test material for its intended application.